



ISO-9001 Certified

UL file No.: E531449

北化院北研科技

BEIHUAYUAN BEIYAN TECHNOLOGY

广东北研新材料科技有限公司

GUANGDONG BEIYAN NEW MATERIALS TECHNOLOGY CO., LTD.

Technical Data Sheet

PA66 BY303G30F

Product description:

Beiyan PA66 BY303G30F is a 30% glass reinforced, flame retardant, modified Polyadiohexylenediamine resin.

Polymeric basis			
Filler / Additive system	30% glass fiber/chemically coupled		
Features	Halogen-free and red phosphorus free flame retardancy, High strength and hardness		
Processing	Injection molding		
RoHS compliance	RoHS compliant		
Properties	Value	Unit	Standard
Density	1.57	g/cm ³	ISO1183
Water absorption 2mm	0.8	%	ISO 62
Shrinkage xFlow 80℃, 48hr	0.4-0.7	%	ISO 294-4
Mechanical properties	Value	Unit	Standard
Tensile stress at break	130	MPa	ISO 527
Elongation break	8	%	ISO 527
Flexural strength	200	MPa	ISO 178
Flexural modulus	6580	MPa	ISO 178
Impact performance	Value	Unit	Standard
Charpy impact strength(notched)	8	KJ/m ²	ISO 179(1eA)
Charpy impact strength (unnotched)	50	KJ/m ²	ISO 179(1eU)
Thermal properties	Value	Unit	Standard
Heat deflection temperature HDT A (1.82MPa)	240	℃	ISO 75f
Electrical	Value	Unit	Standard
Dielectric constant (106Hz)	3.4		IEC 60250
Dissipation factor (106Hz)	1.5×10 ⁻²		IEC 60250
Volume resistivity	1×10 ¹⁴	Ω•m	IEC 60093
Electric strength	33	KV/mm	IEC 60243
CTI	250	V	IEC 60112
Flammability	Value	Unit	Standard
UL flame retardant grade (1.6mm)	V0		UL-94
Injection molding	Value	Unit	Standard
Dry temperature	100-120	℃	
Dry time	4-6	hr	
Processing melt temperature	250-275	℃	
Mold temperature	90-120	℃	

Note: the above data for typical performance index, only for users to select brand reference, not as the products out of the factory acceptance of the legal basis. Users should be used for resin in before test, in order to avoid products are serious or slight defects.

BEIHUAYUAN BEIYAN TECHNOLOGY
Add: Room 601, building 1, No. 770,
Xiegao Road, Xiegang Town, Dongguan
Tel:0769-82858489 Fax: 0769-82858489

BEIYAN
Web: <http://www.bbtrm.com>